
X7R Dielectric

General Specifications



X7R formulations are called “temperature stable” ceramics and fall into EIA Class II materials. X7R is the most popular of these intermediate dielectric constant materials. Its temperature variation of capacitance is within ±15% from -55°C to +125°C. This capacitance change is non-linear.

Capacitance for X7R varies under the influence of electrical operating conditions such as voltage and frequency.


X7R dielectric chip usage covers the broad spectrum of industrial applications where known changes in capacitance due to applied voltages are acceptable.

PART NUMBER (see page 2 for complete part number explanation)


0805	5	C	103	M	A	T	2	A
Size (L" x W")	**Voltage** 4V = 4 6.3V = 6 10V = Z 16V = Y 25V = 3 50V = 5 100V = 1 200V = 2 500V = 7	**Dielectric** X7R = C	**Capacitance Code (In pF)** 2 Sig. Digits + Number of Zeros	**Capacitance Tolerance** J = ± 5%* K = ±10% M = ± 20% *≤1µF only	**Failure Rate** A = Not Applicable	**Terminations** T = Plated Ni and Sn 7 = Gold Plated* Z = FLEXITERM®** *Optional termination **See FLEXITERM® X7R section	**Packaging** 2 = 7" Reel 4 = 13" Reel 7 = Bulk Cass. 9 = Bulk **Contact Factory For Multiples**	**Special Code** A = Std. Product

NOTE: Contact factory for availability of Termination and Tolerance Options for Specific Part Numbers. Contact factory for non-specified capacitance values.


X7R Dielectric
Typical Temperature Coefficient




Δ Capacitance vs. Frequency




Insulation Resistance vs Temperature




Variation of Impedance with Cap Value
Impedance vs. Frequency
1,000 pF vs. 10,000 pF - X7R
0805



Variation of Impedance with Chip Size
Impedance vs. Frequency
10,000 pF - X7R




Variation of Impedance with Chip Size
Impedance vs. Frequency
100,000 pF - X7R



X7R Dielectric

Specifications and Test Methods

Parameter/Test		X7R Specification Limits	Measuring Conditions	
Operating Temperature Range		-55ºC to +125ºC	Temperature Cycle Chamber	
Capacitance		Within specified tolerance	Freq.: 1.0 kHz ± 10% Voltage: 1.0Vrms ± .2V For Cap > 10 µF, 0.5Vrms @ 120Hz	
Dissipation Factor		≤ 2.5% for ≥ 50V DC rating ≤ 3.0% for 25V DC rating ≤ 3.5% for 16V DC rating ≤ 5.0% for ≤ 10V DC rating		
Insulation Resistance		100,000MΩ or 1000MΩ - µF, whichever is less	Charge device with rated voltage for 120 ± 5 secs @ room temp/humidity	
Dielectric Strength		No breakdown or visual defects	Charge device with 300% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max) Note: Charge device with 150% of rated voltage for 500V devices.	
Resistance to Flexure Stresses	Appearance	No defects	Deflection: 2mm Test Time: 30 seconds 	
	Capacitance Variation	≤ ±12%		
	Dissipation Factor	Meets Initial Values (As Above)		
	Insulation Resistance	≥ Initial Value x 0.3		
Solderability		≥ 95% of each terminal should be covered with fresh solder	Dip device in eutectic solder at 230 ± 5ºC for 5.0 ± 0.5 seconds	
Resistance to Solder Heat	Appearance	No defects, <25% leaching of either end terminal	Dip device in eutectic solder at 260ºC for 60 seconds. Store at room temperature for 24 ± 2 hours before measuring electrical properties.	
	Capacitance Variation	≤ ±7.5%		
	Dissipation Factor	Meets Initial Values (As Above)		
	Insulation Resistance	Meets Initial Values (As Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Thermal Shock	Appearance	No visual defects	Step 1: -55ºC ± 2º	30 ± 3 minutes
	Capacitance Variation	≤ ±7.5%	Step 2: Room Temp	≤ 3 minutes
	Dissipation Factor	Meets Initial Values (As Above)	Step 3: +125ºC ± 2º	30 ± 3 minutes
	Insulation Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	≤ 3 minutes
	Dielectric Strength	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 ± 2 hours at room temperature	
Load Life	Appearance	No visual defects	Charge device with 1.5 rated voltage (≤ 10V) in test chamber set at 125ºC ± 2ºC for 1000 hours (+48, -0) Remove from test chamber and stabilize at room temperature for 24 ± 2 hours before measuring.	
	Capacitance Variation	≤ ±12.5%		
	Dissipation Factor	≤ Initial Value x 2.0 (See Above)		
	Insulation Resistance	≥ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Load Humidity	Appearance	No visual defects	Store in a test chamber set at 85ºC ± 2ºC/ 85% ± 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied. Remove from chamber and stabilize at room temperature and humidity for 24 ± 2 hours before measuring.	
	Capacitance Variation	≤ ±12.5%		
	Dissipation Factor	≤ Initial Value x 2.0 (See Above)		
	Insulation Resistance	≥ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		

X7R Dielectric

Capacitance Range

PREFERRED SIZES ARE SHADED

SIZE		0201			0402			0603							0805							1206							
Soldering		Reflow Only			Reflow Only			Reflow Only							Reflow/Wave							Reflow/Wave							
Packaging		All Paper			All Paper			All Paper							Paper/Embossed							Paper/Embossed							
(L) Length	MM	0.60 ± 0.03			1.00 ± 0.10			1.60 ± 0.15							2.01 ± 0.20							3.20 ± 0.20							
	(in.)	(0.024 ± 0.001)			(0.040 ± 0.004)			(0.063 ± 0.006)							(0.079 ± 0.008)							(0.126 ± 0.008)							
(W) Width	MM	0.30 ± 0.03			0.50 ± 0.10			0.81 ± 0.15							1.25 ± 0.20							1.60 ± 0.20							
	(in.)	(0.011 ± 0.001)			(0.020 ± 0.004)			(0.032 ± 0.006)							(0.049 ± 0.008)							(0.063 ± 0.008)							
(t) Terminal	MM	0.15 ± 0.05			0.25 ± 0.15			0.35 ± 0.15							0.50 ± 0.25							0.50 ± 0.25							
	(in.)	(0.006 ± 0.002)			(0.010 ± 0.006)			(0.014 ± 0.006)							(0.020 ± 0.010)							(0.020 ± 0.010)							
	WVDC	10	16	25	16	25	50	6.3	10	16	25	50	100	200	6.3	10	16	25	50	100	200	6.3	10	16	25	50	100	200	500
Cap (pF)	100	A	A	A																									
	150	A	A	A																									
	220	A	A	A			C																						
	330	A	A	A			C					G	G	G		J	J	J	J	J	J								K
	470	A	A				C					G	G	G		J	J	J	J	J	J								K
	680	A	A				C					G	G	G		J	J	J	J	J	J								K
	1000	A	A				C					G	G	G		J	J	J	J	J	J								K
	1500	A					C					G	G			J	J	J	J	J	J		J	J	J	J	J	J	M
	2200	A					C					G	G			J	J	J	J	J	J		J	J	J	J	J	J	M
	3300	A				C	C					G	G			J	J	J	J	J	J		J	J	J	J	J	J	M
	4700	A				C	C					G	G			J	J	J	J	J	J		J	J	J	J	J	J	M
	6800	A			C	C						G	G			J	J	J	J	J	J		J	J	J	J	J	J	P
Cap (µF)	0.010	A			C	C					G	G	G			J	J	J	J	J	J		J	J	J	J	J	J	P
	0.015				C						G	G				J	J	J	J	J	J		J	J	J	J	J	M	
	0.022				C						G	G				J	J	J	J	J	N		J	J	J	J	J	M	
	0.033									G	G	G				J	J	J	J	N			J	J	J	J	J	M	
	0.047									G	G	G				J	J	J	J	N			J	J	J	J	J	M	
	0.068									G	G	G				J	J	J	J	N			J	J	J	J	J	P	
	0.10								G	G	G	G				J	J	J	J	N			J	J	J	J	M	P	
	0.15							G	G							J	J	J	N				J	J	J	J	Q		
	0.22							G	G		J					J	J	N	N				J	J	J	J	Q		
	0.33															N	N	N	N				J	J	M	P	Q		
	0.47															N	N	N	N				M	M	M	P	Q		
	0.68															N	N	N					M	M	Q	Q	Q		
	1.0								J	J						N	N	N					M	M	Q	Q	Q		
	1.5																						P	Q	Q				
	2.2							J										P					Q	Q	Q				
	3.3																												
	4.7															P	P						Q	Q	Q				
	10														P								Q	Q					
	22																					Q							
	47																												
	100																												
	WVDC	10	16	25	16	25	50	6.3	10	16	25	50	100	200	6.3	10	16	25	50	100	200	6.3	10	16	25	50	100	200	500
	SIZE	0201			0402			0603							0805							1206							

Letter	A	C	E	G	J	K	M	N	P	Q	X	Y	Z
Max. Thickness	0.33 (0.013)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)
	PAPER					EMBOSSED							


= Under Development

X7R Dielectric

Capacitance Range

PREFERRED SIZES ARE SHADED

SIZE		1210							1812				1825		2220				2225	
Soldering		Reflow Only							Reflow Only				Reflow Only		Reflow Only				Reflow Only	
Packaging		Paper/Embossed							All Embossed				All Embossed		All Embossed				All Embossed	
(L) Length	MM	3.20 ± 0.20							4.50 ± 0.30				4.50 ± 0.30		5.70 ± 0.40				5.72 ± 0.25	
	(in.)	(0.126 ± 0.008)							(0.177 ± 0.012)				(0.177 ± 0.012)		(0.225 ± 0.016)				(0.225 ± 0.010)	
(W) Width	MM	2.50 ± 0.20							3.20 ± 0.20				6.40 ± 0.40		5.00 ± 0.40				6.35 ± 0.25	
	(in.)	(0.098 ± 0.008)							(0.126 ± 0.008)				(0.252 ± 0.016)		(0.197 ± 0.016)				(0.250 ± 0.010)	
(t) Terminal	MM	0.50 ± 0.25							0.61 ± 0.36				0.61 ± 0.36		0.64 ± 0.39				0.64 ± 0.39	
	(in.)	(0.020 ± 0.010)							(0.024 ± 0.014)				(0.024 ± 0.014)		(0.025 ± 0.015)				(0.025 ± 0.015)	
	WVDC	10	16	25	50	100	200	500	50	100	200	500	50	100	25	50	100	200	50	100
Cap (pF)	100																			
	150																			
	220																			
	330																			
	470																			
	680																			
	1000																			
	1500	J	J	J	J	J	J	M												
	2200	J	J	J	J	J	J	M												
	3300	J	J	J	J	J	J	M												
	4700	J	J	J	J	J	J	M												
	6800	J	J	J	J	J	J	M												
Cap (µF)	0.010	J	J	J	J	J	J	M	K	K	K	K	M	M		X	X	X	M	P
	0.015	J	J	J	J	J	J	P	K	K	K	P	M	M		X	X	X	M	P
	0.022	J	J	J	J	J	J	Q	K	K	K	P	M	M		X	X	X	M	P
	0.033	J	J	J	J	J	J	Q	K	K	K	X	M	M		X	X	X	M	P
	0.047	J	J	J	J	J	J		K	K	K	Z	M	M		X	X	X	M	P
	0.068	J	J	J	J	J	M		K	K	K	Z	M	M		X	X	X	M	P
	0.10	J	J	J	J	J	M		K	K	K	Z	M	M		X	X	X	M	P
	0.15	J	J	J	J	M			K	K	P		M	M		X	X	X	M	P
	0.22	J	J	J	J	P			K	K	P		M	M		X	X		M	P
	0.33	J	J	J	J	Z			K	M			M	M		X	X		M	P
	0.47	M	M	M	M	Z			K	P			M	M		X	X		M	P
	0.68	M	M	P	X	Z			M	Q			M	P		X	X		M	P
	1.0	N	N	P	X	Z			M	X			M	P		X	Z		M	P
	1.5	N	N	Z	Z	Z			Z	Z			M			X	Z		M	X
	2.2	X	X	Z	Z	Z			Z	Z						X			M	
	3.3	X	X	Z	Z				Z							X				
	4.7	X	X	Z	Z				Z							X				
	10	Z	Z	Z												Z				
	22	Z	Z												Z					
	47																			
	100																			
	WVDC	10	16	25	50	100	200	500	50	100	200	500	50	100	25	50	100	200	50	100
SIZE		1210							1812				1825		2220				2225	



Letter	A	C	E	G	J	K	M	N	P	Q	X	Y	Z
Max. Thickness	0.33 (0.013)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)
	PAPER					EMBOSSED							

= Under Development

ООО «НИОКРсистемс» - это оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов. Реализуемая нашей компанией продукция насчитывает более полумиллиона наименований.

Благодаря этому наша компания предлагает к поставке практически не ограниченный ассортимент компонентов как оптовыми, мелкооптовыми партиями, так и в розницу.

Благодаря развитой сети поставщиков, помогаем в поиске и приобретении экзотичных или снятых с производства компонентов.

Наша компания это:

- Гарантия качества поставляемой продукции
- Широкий ассортимент
- Минимальные сроки поставок
- Техническая поддержка
- Подбор комплектации
- Индивидуальный подход
- Гибкое ценообразование
- Работаем по 275 ФЗ

ООО «НИОКР СИТЕМС»
Москва, 125362, Россия, ул. Вишневая, д. 9, к. 1, Блок 104 а и 104 в

Телефон: 8 (495) 268-14-82
Email: n@nsistems.ru

ИНН: 7735154786
ОГРН: 1167746717709