



Easy Profile® 256 No-Clean Solderpaste

Product Description

Easy Profile® 256 is a no-clean, air or nitrogen reflowable, solder paste specifically designed for maximum robustness in reflow profiling and stencil printing. EP256 has the widest possible reflow processing window. EP256 is also capable of stencil printing downtimes of up to 90 minutes with an effective first print down to 20 mils. EP256 is a solderpaste formula that maintains its activity and printing characteristics for up to 8 hours without any shear thinning.

- Stable wetting behavior over a wide range of profiles
- Capable of 90 minute break times in printing
- High print speeds to 200+ mm/sec (8+ in/sec)
- Compatible with enclosed print head systems
- Excellent printing characteristics to 0.4mm (16 mil) pitch with Type 3 powder
- High activity on all substrates, including OSPs
- Capable of off-pad printing with no solderballs after reflow
- Stencil life: 8+ hours (process dependent)
- Scrap is reduced due to less paste dry out
- Stable tack over 8+ hours
- Classified as ROL0 per J-STD-004
- Compliant to Bellcore GR-78

Standard Applications

90% Metal - Stencil Printing

90% Metal - Enclosed Head Printing

Physical Properties

(Data given for Sn63Pb37 90% metal, -325+500 mesh)

Viscosity (typical): 1400 poise

Malcom Viscometer @ 10rpm and 25°C

Initial Tackiness (typical): 40 grams

Tested to Kester Method 1W-QC-3-04

Slump Test: Pass

Tested to J-STD-005, IPC-TM-650, Method 2.4.35

Solder Ball Test: Pass

Tested to J-STD-005, IPC-TM-650, Method 2.4.43

Wetting Test: Pass

Tested to J-STD-005, IPC-TM-650, Method 2.4.45

Reliability Properties

Copper Mirror Corrosion: Low

Tested to J-STD-004, IPC-TM-650, Method 2.3.3

Corrosion Test: Low

Tested to J-STD-004, IPC-TM-650, Method 2.6.15

Silver Chromate: Pass

Tested to J-STD-004, IPC-TM-650, Method 2.3.33

Chloride and Bromides: None Detected

Tested to J-STD-004, IPC-TM-650, Method 2.3.35

Fluorides by Spot Test: Pass

Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1

SIR, IPC (typical): Pass

Tested to J-STD-004, IPC-TM-650, Method 2.6.3.3

	Blank	EP256
Day 1	$1.0 \times 10^{10} \Omega$	$9.8 \times 10^8 \Omega$
Day 4	$1.3 \times 10^{10} \Omega$	$1.6 \times 10^9 \Omega$
Day 7	$1.3 \times 10^{10} \Omega$	$1.1 \times 10^9 \Omega$

Application Notes

Availability:


Easy Profile® 256 is commonly available in the Sn63Pb37 and Sn62Pb36Ag02 alloys. Type 3 powder mesh is recommended, but different powder particle size distributions are available for standard and fine pitch applications. For specific packaging information, see Kester's Solder Paste Chart for available sizes. The appropriate combination depends on process variables and the specific application.

Printing Parameters:

Squeegee Blade	80 to 90 durometer polyurethane or stainless steel
Squeegee Speed	Capable to a maximum speed of 200 mm/sec (8 in/sec)
Stencil Material	Stainless Steel, Molybdenum, Nickel Plated, Brass
Temperature/Humidity	Optimal ranges are 21-25°C (70-77°F) and 35-65% R.H.

Recommended Reflow Profile:

The recommended reflow profile for EP256 made with either the Sn63Pb37 or Sn62Pb36Ag02 is shown here. This profile is simply a guideline. Since EP256 is a highly active solder paste, it can solder effectively over a wide range of profiles. Your optimal profile may be different from the one shown based on your oven, board and mix of defects. Please contact Kester if you need additional profiling advice.



Cleaning:

EP256 is a no-clean formula. The residues don't need to be removed for typical applications. Although EP256 is designed for no-clean applications, its residues can be easily removed using automated cleaning equipment (in-line or batch) with a variety of readily available cleaning agents. Call Kester Technical Support for details.

Storage, Handling, and Shelf Life:

Refrigeration is the recommended optimum storage condition for solderpaste to maintain consistent viscosity, reflow characteristics and overall performance. EP256 should be stabilized at room temperature prior to printing. EP256 should be kept at standard refrigeration conditions, 0-10°C (32-50°F). Please contact Kester if you require additional advice with regard storage and handling of this material. Shelf life is 6 months from date of manufacture when handled properly when held at 0-10°C (32-50°F).

Health & Safety:

This product, during handling or use, may be hazardous to health or the environment. Read the Material Safety Data Sheet and warning label before using this product.

World Headquarters: 800 West Thorndale Avenue, Itasca, Illinois, 60143-1341 USA
Phone: (+1) 630-616-4000 • **Email:** customerservice@kester.com • **Website:** www.kester.com

Asia Pacific Headquarters
 500 Chai Chee Lane
 Singapore 469024
 (+65) 6449-1133
 customerservice@kester.com.sg

European Headquarters
 Ganghoferstrasse 45
 D-82216 Gernlinden
 Germany
 (+49) 8142-47850
 customerservice@kester-eu.com

Japanese Headquarters
 20-11 Yokokawa 2-Chome
 Sumida-Ku
 Tokyo 130-0003 Japan
 (+81) 3-3624-5351
 jpsales@kester.com.sg

The data recommendations presented are based on tests, which we consider reliable. Because Kester has no control over the conditions of use, we disclaim any responsibility connected with the use of any of our products or the information presented. We advise that all chemical products be used only by or under the direction of technically qualified personnel who are aware of the potential hazards involved and the necessity for reasonable care in their handling. The technical information contained herein is consistent with the properties of this material but should not be used in the preparation of specifications as it is intended for reference only. For assistance in preparing specifications, please contact your local Kester office for details.



ООО «НИОКРсистемс» - это оперативные поставки широкого спектра электронных компонентов отечественного и импортного производства напрямую от производителей и с крупнейших мировых складов. Реализуемая нашей компанией продукция насчитывает более полумиллиона наименований.

Благодаря этому наша компания предлагает к поставке практически не ограниченный ассортимент компонентов как оптовыми, мелкооптовыми партиями, так и в розницу.

Благодаря развитой сети поставщиков, помогаем в поиске и приобретении экзотичных или снятых с производства компонентов.

Наша компания это:

- Гарантия качества поставляемой продукции
- Широкий ассортимент
- Минимальные сроки поставок
- Техническая поддержка
- Подбор комплектации
- Индивидуальный подход
- Гибкое ценообразование
- Работаем по 275 ФЗ